


## Flexure Test



Specimen Name
CF65CNT5_COMP_1

	Specimen label	Rate 1 (mm/min)	Support span (mm)	Thickness (mm)	Width (mm)
1	CF65CNT5_COMP_1	1.00000	60.00000		
Coefficient of Variation		-----	-----		
Maximum		1.00000	60.00000		
Mean		1.00000	60.00000		
Median		1.00000	60.00000		
Minimum		1.00000	60.00000		
Range		0.00000	0.00000		
Standard Deviation		-----	-----		

	Flex ext at Break (Standard) (mm)	Flex stress at Max Flex load (MPa)	Max Flexure load (N)	Flex ext at Max Flex load (mm)	Flex strain at Max Flex load (mm/mm)
1	2.33593	151.609	124.03518	2.056	0.017
Coefficient of Variation	-----	-----	-----	-----	-----
Maximum	2.33593	151.609	124.03518	2.056	0.017
Mean	2.33593	151.609	124.03518	2.056	0.017
Median	2.33593	151.609	124.03518	2.056	0.017
Minimum	2.33593	151.609	124.03518	2.056	0.017
Range	0.00000	0.000	0.00000	0.000	0.000
Standard Deviation	-----	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
1	33662.21	8.579	10.486	8568.758
Coefficient of Variation	-----	-----	-----	-----
Maximum	33662.21	8.579	10.486	8568.758
Mean	33662.21	8.579	10.486	8568.758
Median	33662.21	8.579	10.486	8568.758
Minimum	33662.21	8.579	10.486	8568.758
Range	0.00	0.000	0.000	0.000

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
Standard Deviation	-----	-----	-----	-----