


## Flexure Test



Specimen Name  
CF65CNT5\_COMP\_2

	Specimen label	Rate 1 (mm/min)	Support span (mm)	Thickness (mm)	Width (mm)
1	CF65CNT5_COMP_2	1.00000	60.00000		
Coefficient of Variation		-----	-----		
Maximum		1.00000	60.00000		
Mean		1.00000	60.00000		
Median		1.00000	60.00000		
Minimum		1.00000	60.00000		
Range		0.00000	0.00000		
Standard Deviation		-----	-----		

	Flex ext at Break (Standard) (mm)	Flex stress at Max Flex load (MPa)	Max Flexure load (N)	Flex ext at Max Flex load (mm)	Flex strain at Max Flex load (mm/mm)
1	0.45482	19.862	16.24993	0.410	0.003
Coefficient of Variation	-----	-----	-----	-----	-----
Maximum	0.45482	19.862	16.24993	0.410	0.003
Mean	0.45482	19.862	16.24993	0.410	0.003
Median	0.45482	19.862	16.24993	0.410	0.003
Minimum	0.45482	19.862	16.24993	0.410	0.003
Range	0.00000	0.000	0.00000	0.000	0.000
Standard Deviation	-----	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
1	11916.72	-----	-----	-----
Coefficient of Variation	-----	-----	-----	-----
Maximum	11916.72	-----	-----	-----
Mean	11916.72	-----	-----	-----
Median	11916.72	-----	-----	-----
Minimum	11916.72	-----	-----	-----
Range	0.00	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
Standard Deviation	-----	-----	-----	-----