


Flexure Test



Specimen Name	
—	CF65CNT5_COMP_2

	Specimen label	Rate 1 (mm/min)	Support span (mm)	Thickness (mm)	Width (mm)
1	CF65CNT5_COMP_2	1.00000	60.00000		
Coefficient of Variation		-----	-----		
Maximum		1.00000	60.00000		
Mean		1.00000	60.00000		
Median		1.00000	60.00000		
Minimum		1.00000	60.00000		
Range		0.00000	0.00000		
Standard Deviation		-----	-----		

	Flex ext at Break (Standard) (mm)	Flex stress at Max Flex load (MPa)	Max Flexure load (N)	Flex ext at Max Flex load (mm)	Flex strain at Max Flex load (mm/mm)
1	0.45445	19.744	16.15271	0.394	0.003
Coefficient of Variation	-----	-----	-----	-----	-----
Maximum	0.45445	19.744	16.15271	0.394	0.003
Mean	0.45445	19.744	16.15271	0.394	0.003
Median	0.45445	19.744	16.15271	0.394	0.003
Minimum	0.45445	19.744	16.15271	0.394	0.003
Range	0.00000	0.000	0.00000	0.000	0.000
Standard Deviation	-----	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
1	14983.14	16.153	19.744	-----
Coefficient of Variation	-----	-----	-----	-----
Maximum	14983.14	16.153	19.744	-----
Mean	14983.14	16.153	19.744	-----
Median	14983.14	16.153	19.744	-----
Minimum	14983.14	16.153	19.744	-----
Range	0.00	0.000	0.000	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
Standard Deviation	-----	-----	-----	-----