


Flexure Test



Specimen Name
CF65Gp5_2

	Specimen label	Rate 1 (mm/min)	Support span (mm)	Thickness (mm)	Width (mm)
1	CF65Gp5_2	1.00000	72.00000		
Coefficient of Variation		-----	-----		
Maximum		1.00000	72.00000		
Mean		1.00000	72.00000		
Median		1.00000	72.00000		
Minimum		1.00000	72.00000		
Range		0.00000	0.00000		
Standard Deviation		-----	-----		

	Flex ext at Break (Standard) (mm)	Flex stress at Max Flex load (MPa)	Max Flexure load (N)	Flex ext at Max Flex load (mm)	Flex strain at Max Flex load (mm/mm)
1	2.20612	127.598	86.99211	2.173	0.013
Coefficient of Variation	-----	-----	-----	-----	-----
Maximum	2.20612	127.598	86.99211	2.173	0.013
Mean	2.20612	127.598	86.99211	2.173	0.013
Median	2.20612	127.598	86.99211	2.173	0.013
Minimum	2.20612	127.598	86.99211	2.173	0.013
Range	0.00000	0.000	0.00000	0.000	0.000
Standard Deviation	-----	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
1	20774.63	11.715	17.183	-----
Coefficient of Variation	-----	-----	-----	-----
Maximum	20774.63	11.715	17.183	-----
Mean	20774.63	11.715	17.183	-----
Median	20774.63	11.715	17.183	-----
Minimum	20774.63	11.715	17.183	-----
Range	0.00	0.000	0.000	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
Standard Deviation	-----	-----	-----	-----