


Flexure Test



Specimen Name	
	A

	Specimen label	Rate 1 (mm/min)	Support span (mm)	Thickness (mm)	Width (mm)
1	A	1.00000	72.00000		
Coefficient of Variation		-----	-----		
Maximum		1.00000	72.00000		
Mean		1.00000	72.00000		
Median		1.00000	72.00000		
Minimum		1.00000	72.00000		
Range		0.00000	0.00000		
Standard Deviation		-----	-----		

	Flex ext at Break (Standard) (mm)	Flex stress at Max Flex load (MPa)	Max Flexure load (N)	Flex ext at Max Flex load (mm)	Flex strain at Max Flex load (mm/mm)
1	0.58195	22.028	15.01829	0.519	0.003
Coefficient of Variation	-----	-----	-----	-----	-----
Maximum	0.58195	22.028	15.01829	0.519	0.003
Mean	0.58195	22.028	15.01829	0.519	0.003
Median	0.58195	22.028	15.01829	0.519	0.003
Minimum	0.58195	22.028	15.01829	0.519	0.003
Range	0.00000	0.000	0.00000	0.000	0.000
Standard Deviation	-----	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
1	6193.93	1.658	2.432	-----
Coefficient of Variation	-----	-----	-----	-----
Maximum	6193.93	1.658	2.432	-----
Mean	6193.93	1.658	2.432	-----
Median	6193.93	1.658	2.432	-----
Minimum	6193.93	1.658	2.432	-----
Range	0.00	0.000	0.000	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
Standard Deviation	-----	-----	-----	-----