


Flexure Test



Specimen Name
CF70CNT5_COM_1

	Specimen label	Rate 1 (mm/min)	Support span (mm)	Thickness (mm)	Width (mm)
1	CF70CNT5_COM_1	1.00000	60.00000		
Coefficient of Variation		-----	-----		
Maximum		1.00000	60.00000		
Mean		1.00000	60.00000		
Median		1.00000	60.00000		
Minimum		1.00000	60.00000		
Range		0.00000	0.00000		
Standard Deviation		-----	-----		

	Flex ext at Break (Standard) (mm)	Flex stress at Max Flex load (MPa)	Max Flexure load (N)	Flex ext at Max Flex load (mm)	Flex strain at Max Flex load (mm/mm)
1	2.28123	96.539	78.98044	1.816	0.015
Coefficient of Variation	-----	-----	-----	-----	-----
Maximum	2.28123	96.539	78.98044	1.816	0.015
Mean	2.28123	96.539	78.98044	1.816	0.015
Median	2.28123	96.539	78.98044	1.816	0.015
Minimum	2.28123	96.539	78.98044	1.816	0.015
Range	0.00000	0.000	0.00000	0.000	0.000
Standard Deviation	-----	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
1	12320.05	78.980	96.539	8086.857
Coefficient of Variation	-----	-----	-----	-----
Maximum	12320.05	78.980	96.539	8086.857
Mean	12320.05	78.980	96.539	8086.857
Median	12320.05	78.980	96.539	8086.857
Minimum	12320.05	78.980	96.539	8086.857
Range	0.00	0.000	0.000	0.000

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
Standard Deviation	-----	-----	-----	-----