


## Flexure Test



Specimen Name
CF70CNT5_COM_2

	Specimen label	Rate 1 (mm/min)	Support span (mm)	Thickness (mm)	Width (mm)
1	CF70CNT5_COM_2	1.00000	60.00000		
Coefficient of Variation		-----	-----		
Maximum		1.00000	60.00000		
Mean		1.00000	60.00000		
Median		1.00000	60.00000		
Minimum		1.00000	60.00000		
Range		0.00000	0.00000		
Standard Deviation		-----	-----		

	Flex ext at Break (Standard) (mm)	Flex stress at Max Flex load (MPa)	Max Flexure load (N)	Flex ext at Max Flex load (mm)	Flex strain at Max Flex load (mm/mm)
1	0.57198	36.281	29.68238	0.562	0.005
Coefficient of Variation	-----	-----	-----	-----	-----
Maximum	0.57198	36.281	29.68238	0.562	0.005
Mean	0.57198	36.281	29.68238	0.562	0.005
Median	0.57198	36.281	29.68238	0.562	0.005
Minimum	0.57198	36.281	29.68238	0.562	0.005
Range	0.00000	0.000	0.00000	0.000	0.000
Standard Deviation	-----	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
1	16741.83	29.682	36.281	-----
Coefficient of Variation	-----	-----	-----	-----
Maximum	16741.83	29.682	36.281	-----
Mean	16741.83	29.682	36.281	-----
Median	16741.83	29.682	36.281	-----
Minimum	16741.83	29.682	36.281	-----
Range	0.00	0.000	0.000	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
Standard Deviation	-----	-----	-----	-----