


Flexure Test



Specimen Name
CF70CNT5_COMP_3

	Specimen label	Rate 1 (mm/min)	Support span (mm)	Thickness (mm)	Width (mm)
1	CF70CNT5_COMP_3	1.00000	60.00000		
Coefficient of Variation		-----	-----		
Maximum		1.00000	60.00000		
Mean		1.00000	60.00000		
Median		1.00000	60.00000		
Minimum		1.00000	60.00000		
Range		0.00000	0.00000		
Standard Deviation		-----	-----		

	Flex ext at Break (Standard) (mm)	Flex stress at Max Flex load (MPa)	Max Flexure load (N)	Flex ext at Max Flex load (mm)	Flex strain at Max Flex load (mm/mm)
1	0.49870	27.983	22.89393	0.459	0.004
Coefficient of Variation	-----	-----	-----	-----	-----
Maximum	0.49870	27.983	22.89393	0.459	0.004
Mean	0.49870	27.983	22.89393	0.459	0.004
Median	0.49870	27.983	22.89393	0.459	0.004
Minimum	0.49870	27.983	22.89393	0.459	0.004
Range	0.00000	0.000	0.00000	0.000	0.000
Standard Deviation	-----	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
1	13868.09	22.894	27.983	-----
Coefficient of Variation	-----	-----	-----	-----
Maximum	13868.09	22.894	27.983	-----
Mean	13868.09	22.894	27.983	-----
Median	13868.09	22.894	27.983	-----
Minimum	13868.09	22.894	27.983	-----
Range	0.00	0.000	0.000	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
Standard Deviation	-----	-----	-----	-----