


## Flexure Test



Specimen Name  
— CF70CNT5\_COMP\_4

	Specimen label	Rate 1 (mm/min)	Support span (mm)	Thickness (mm)	Width (mm)
1	CF70CNT5_COMP_4	1.00000	60.00000		
Coefficient of Variation		-----	-----		
Maximum		1.00000	60.00000		
Mean		1.00000	60.00000		
Median		1.00000	60.00000		
Minimum		1.00000	60.00000		
Range		0.00000	0.00000		
Standard Deviation		-----	-----		

	Flex ext at Break (Standard) (mm)	Flex stress at Max Flex load (MPa)	Max Flexure load (N)	Flex ext at Max Flex load (mm)	Flex strain at Max Flex load (mm/mm)
1	1.69039	120.702	98.74942	1.585	0.013
Coefficient of Variation	-----	-----	-----	-----	-----
Maximum	1.69039	120.702	98.74942	1.585	0.013
Mean	1.69039	120.702	98.74942	1.585	0.013
Median	1.69039	120.702	98.74942	1.585	0.013
Minimum	1.69039	120.702	98.74942	1.585	0.013
Range	0.00000	0.000	0.00000	0.000	0.000
Standard Deviation	-----	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
1	31463.97	6.037	7.379	9163.794
Coefficient of Variation	-----	-----	-----	-----
Maximum	31463.97	6.037	7.379	9163.794
Mean	31463.97	6.037	7.379	9163.794
Median	31463.97	6.037	7.379	9163.794
Minimum	31463.97	6.037	7.379	9163.794
Range	0.00	0.000	0.000	0.000

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
Standard Deviation	-----	-----	-----	-----