


Flexure Test



	Specimen label	Rate 1 (mm/min)	Support span (mm)	Thickness (mm)	Width (mm)
1	CF70Gp5_1	1.00000	72.00000		
Coefficient of Variation		-----	-----		
Maximum		1.00000	72.00000		
Mean		1.00000	72.00000		
Median		1.00000	72.00000		
Minimum		1.00000	72.00000		
Range		0.00000	0.00000		
Standard Deviation		-----	-----		

	Flex ext at Break (Standard) (mm)	Flex stress at Max Flex load (MPa)	Max Flexure load (N)	Flex ext at Max Flex load (mm)	Flex strain at Max Flex load (mm/mm)
1	1.55528	160.887	109.68793	1.535	0.009
Coefficient of Variation	-----	-----	-----	-----	-----
Maximum	1.55528	160.887	109.68793	1.535	0.009
Mean	1.55528	160.887	109.68793	1.535	0.009
Median	1.55528	160.887	109.68793	1.535	0.009
Minimum	1.55528	160.887	109.68793	1.535	0.009
Range	0.00000	0.000	0.00000	0.000	0.000
Standard Deviation	-----	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
1	53832.42	9.280	13.611	7523.988
Coefficient of Variation	-----	-----	-----	-----
Maximum	53832.42	9.280	13.611	7523.988
Mean	53832.42	9.280	13.611	7523.988
Median	53832.42	9.280	13.611	7523.988
Minimum	53832.42	9.280	13.611	7523.988
Range	0.00	0.000	0.000	0.000

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
Standard Deviation	-----	-----	-----	-----