


## Flexure Test



Specimen Name
CF70Gp5_2

	Specimen label	Rate 1 (mm/min)	Support span (mm)	Thickness (mm)	Width (mm)
1	CF70Gp5_2	1.00000	72.00000		
Coefficient of Variation		-----	-----		
Maximum		1.00000	72.00000		
Mean		1.00000	72.00000		
Median		1.00000	72.00000		
Minimum		1.00000	72.00000		
Range		0.00000	0.00000		
Standard Deviation		-----	-----		

	Flex ext at Break (Standard) (mm)	Flex stress at Max Flex load (MPa)	Max Flexure load (N)	Flex ext at Max Flex load (mm)	Flex strain at Max Flex load (mm/mm)
1	1.99832	167.824	114.41750	1.975	0.011
Coefficient of Variation	-----	-----	-----	-----	-----
Maximum	1.99832	167.824	114.41750	1.975	0.011
Mean	1.99832	167.824	114.41750	1.975	0.011
Median	1.99832	167.824	114.41750	1.975	0.011
Minimum	1.99832	167.824	114.41750	1.975	0.011
Range	0.00000	0.000	0.00000	0.000	0.000
Standard Deviation	-----	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
1	25729.45	5.715	8.382	36634.259
Coefficient of Variation	-----	-----	-----	-----
Maximum	25729.45	5.715	8.382	36634.259
Mean	25729.45	5.715	8.382	36634.259
Median	25729.45	5.715	8.382	36634.259
Minimum	25729.45	5.715	8.382	36634.259
Range	0.00	0.000	0.000	0.000

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
Standard Deviation	-----	-----	-----	-----