


Flexure Test



	Specimen label	Rate 1 (mm/min)	Support span (mm)	Thickness (mm)	Width (mm)
1	CF70Gp_3	1.00000	72.00000		
Coefficient of Variation		-----	-----		
Maximum		1.00000	72.00000		
Mean		1.00000	72.00000		
Median		1.00000	72.00000		
Minimum		1.00000	72.00000		
Range		0.00000	0.00000		
Standard Deviation		-----	-----		

	Flex ext at Break (Standard) (mm)	Flex stress at Max Flex load (MPa)	Max Flexure load (N)	Flex ext at Max Flex load (mm)	Flex strain at Max Flex load (mm/mm)
1	3.96632	122.873	83.77096	3.921	0.023
Coefficient of Variation	-----	-----	-----	-----	-----
Maximum	3.96632	122.873	83.77096	3.921	0.023
Mean	3.96632	122.873	83.77096	3.921	0.023
Median	3.96632	122.873	83.77096	3.921	0.023
Minimum	3.96632	122.873	83.77096	3.921	0.023
Range	0.00000	0.000	0.00000	0.000	0.000
Standard Deviation	-----	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
1	30380.68	4.961	7.277	24245.987
Coefficient of Variation	-----	-----	-----	-----
Maximum	30380.68	4.961	7.277	24245.987
Mean	30380.68	4.961	7.277	24245.987
Median	30380.68	4.961	7.277	24245.987
Minimum	30380.68	4.961	7.277	24245.987
Range	0.00	0.000	0.000	0.000

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
Standard Deviation	-----	-----	-----	-----