


## Flexure Test



	Specimen label	Rate 1 (mm/min)	Support span (mm)	Thickness (mm)	Width (mm)
1	65_1	1.00000	72.00000		
Coefficient of Variation		-----	-----		
Maximum		1.00000	72.00000		
Mean		1.00000	72.00000		
Median		1.00000	72.00000		
Minimum		1.00000	72.00000		
Range		0.00000	0.00000		
Standard Deviation		-----	-----		

	Flex ext at Break (Standard) (mm)	Flex stress at Max Flex load (MPa)	Max Flexure load (N)	Flex ext at Max Flex load (mm)	Flex strain at Max Flex load (mm/mm)
1	1.97416	100.512	68.52612	1.929	0.011
Coefficient of Variation	-----	-----	-----	-----	-----
Maximum	1.97416	100.512	68.52612	1.929	0.011
Mean	1.97416	100.512	68.52612	1.929	0.011
Median	1.97416	100.512	68.52612	1.929	0.011
Minimum	1.97416	100.512	68.52612	1.929	0.011
Range	0.00000	0.000	0.00000	0.000	0.000
Standard Deviation	-----	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
1	16771.40	68.526	100.512	20487.231
Coefficient of Variation	-----	-----	-----	-----
Maximum	16771.40	68.526	100.512	20487.231
Mean	16771.40	68.526	100.512	20487.231
Median	16771.40	68.526	100.512	20487.231
Minimum	16771.40	68.526	100.512	20487.231
Range	0.00	0.000	0.000	0.000

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
Standard Deviation	-----	-----	-----	-----