


Flexure Test



	Specimen label	Rate 1 (mm/min)	Support span (mm)	Thickness (mm)	Width (mm)
1	65_2	1.00000	72.00000		
Coefficient of Variation		-----	-----		
Maximum		1.00000	72.00000		
Mean		1.00000	72.00000		
Median		1.00000	72.00000		
Minimum		1.00000	72.00000		
Range		0.00000	0.00000		
Standard Deviation		-----	-----		

	Flex ext at Break (Standard) (mm)	Flex stress at Max Flex load (MPa)	Max Flexure load (N)	Flex ext at Max Flex load (mm)	Flex strain at Max Flex load (mm/mm)
1	1.77209	100.794	68.71806	1.725	0.010
Coefficient of Variation	-----	-----	-----	-----	-----
Maximum	1.77209	100.794	68.71806	1.725	0.010
Mean	1.77209	100.794	68.71806	1.725	0.010
Median	1.77209	100.794	68.71806	1.725	0.010
Minimum	1.77209	100.794	68.71806	1.725	0.010
Range	0.00000	0.000	0.00000	0.000	0.000
Standard Deviation	-----	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
1	22109.69	68.718	100.794	18390.932
Coefficient of Variation	-----	-----	-----	-----
Maximum	22109.69	68.718	100.794	18390.932
Mean	22109.69	68.718	100.794	18390.932
Median	22109.69	68.718	100.794	18390.932
Minimum	22109.69	68.718	100.794	18390.932
Range	0.00	0.000	0.000	0.000

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
Standard Deviation	-----	-----	-----	-----