


Flexure Test



	Specimen label	Rate 1 (mm/min)	Support span (mm)	Thickness (mm)	Width (mm)
1	65_3	1.00000	72.00000		
Coefficient of Variation		-----	-----		
Maximum		1.00000	72.00000		
Mean		1.00000	72.00000		
Median		1.00000	72.00000		
Minimum		1.00000	72.00000		
Range		0.00000	0.00000		
Standard Deviation		-----	-----		

	Flex ext at Break (Standard) (mm)	Flex stress at Max Flex load (MPa)	Max Flexure load (N)	Flex ext at Max Flex load (mm)	Flex strain at Max Flex load (mm/mm)
1	1.77182	99.636	67.92894	1.730	0.010
Coefficient of Variation	-----	-----	-----	-----	-----
Maximum	1.77182	99.636	67.92894	1.730	0.010
Mean	1.77182	99.636	67.92894	1.730	0.010
Median	1.77182	99.636	67.92894	1.730	0.010
Minimum	1.77182	99.636	67.92894	1.730	0.010
Range	0.00000	0.000	0.00000	0.000	0.000
Standard Deviation	-----	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
1	27293.83	31.889	46.775	19790.497
Coefficient of Variation	-----	-----	-----	-----
Maximum	27293.83	31.889	46.775	19790.497
Mean	27293.83	31.889	46.775	19790.497
Median	27293.83	31.889	46.775	19790.497
Minimum	27293.83	31.889	46.775	19790.497
Range	0.00	0.000	0.000	0.000

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
Standard Deviation	-----	-----	-----	-----