


Flexure Test



	Specimen label	Rate 1 (mm/min)	Support span (mm)	Thickness (mm)	Width (mm)
1	70_1	1.00000	72.00000		
Coefficient of Variation		-----	-----		
Maximum		1.00000	72.00000		
Mean		1.00000	72.00000		
Median		1.00000	72.00000		
Minimum		1.00000	72.00000		
Range		0.00000	0.00000		
Standard Deviation		-----	-----		

	Flex ext at Break (Standard) (mm)	Flex stress at Max Flex load (MPa)	Max Flexure load (N)	Flex ext at Max Flex load (mm)	Flex strain at Max Flex load (mm/mm)
1	5.30930	58.360	39.78796	5.124	0.030
Coefficient of Variation	-----	-----	-----	-----	-----
Maximum	5.30930	58.360	39.78796	5.124	0.030
Mean	5.30930	58.360	39.78796	5.124	0.030
Median	5.30930	58.360	39.78796	5.124	0.030
Minimum	5.30930	58.360	39.78796	5.124	0.030
Range	0.00000	0.000	0.00000	0.000	0.000
Standard Deviation	-----	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
1	10048.77	32.592	47.806	8131.667
Coefficient of Variation	-----	-----	-----	-----
Maximum	10048.77	32.592	47.806	8131.667
Mean	10048.77	32.592	47.806	8131.667
Median	10048.77	32.592	47.806	8131.667
Minimum	10048.77	32.592	47.806	8131.667
Range	0.00	0.000	0.000	0.000

	Modulus (Automatic) (MPa)	Flex load at Yield (Zero Slope) (N)	Flex stress at Yield (Zero Slope) (MPa)	Modulus (E-modulus) (MPa)
Standard Deviation	-----	-----	-----	-----